

FGWPET50-W58ORD

Face Material

weight	thickness	material
65g / m ² ± 10% ISO536	0.045mm ± 10% ISO534	Gloss white polyester film

Liner

58g / m ² ± 10% ISO536	0.05mm ± 10% ISO534	white glassine paper with super calender treatment
-----------------------------------	---------------------	--

Adhesive

ORD is a removable adhesive. It has proper initial viscosity and high resilience. It has good final removability and viscosity. It can be torn and pasted on many non-paper stickers without leaving residual glue. The normal use range is wide.

Peel adhesion

initial adhesion 7 N/25mm or tear off FTM9	20 mins Peel adhesion value on steel at 180 angle 8 N/25mm or tear off FTM1	20 mins Peel adhesion value on steel at 90 angle 5.5N/25mm or tear off FTM2
---	---	---

Temperature

Min. Appl. Temp. 0 °C	Service Temp. -30°C +80°C (24H after labeling)
-----------------------	--

Applications

The product has excellent tear resistance, dimensional stability and chemical corrosion resistance, and is suitable for making various durability labels.

The above suggestion, application, and elaboration are not intended as the guarantee of Jinya. All sales of Jinya products shall be tested by customer in the final environment to confirm compliance with the requirements of the use of environment.

Printing Methods

After special coating treatment, the surface can meet various printing methods without special ink treatment. Suitable for carbon tape printing. It is recommended to use high hardness tools for die cutting, and colleagues should avoid label overflow due to excessive winding tension.

Shelf life

12 months, applicable only to the material delivered by Jinya which has not undergone further processing, under the following **STORAGE CONDITIONS**:

- This material must be stored at a temperature of 23 ± 2°C and 50 ± 5% of Relative Humidity.
- Storage area must be dry and clean.
- Keep the material in the original packaging when not used in order to protect it from dust and contamination.
- Do not expose to direct sunlight or heat sources.