

PWF60-WC55ER

Face Material

weight	thickness	material
60 ± 10%g/m ² ISO 536	0.07 ± 10%mm ISO 534	uncoated white matt paper

Liner

55 ± 10%g/m ² ISO 536	0.055 ± 10%mm ISO 534	Single-color plastic-coated white CCK release paper
----------------------------------	-----------------------	---

Adhesive

This is a removable weak sticky adhesive with weak sticky acrylic adhesive, not suitable for repeated sticking. Peel off without adhesive residue. Not suitable for sticking PE bags and oily surface substrates, suitable for short-term sticking quality.

Peel adhesion

Initial adhesion 5N/25mm FTM 9 st.st	20 minutes Peel adhesion value on steel at 180° 3.5N/25mm or tear off FTM 1 st.st	20 minutes Peel adhesion value on steel at 90° 3N/25mm or tear off FTM 2 st.st
---	---	--

Temperature

Min. Appl. Temp. 10 °C	Service Temp. 0°C+90°C (after 24hrs)
------------------------	--------------------------------------

Applications

This is a weak acrylic adhesive, not suitable for repeated application. It is not suitable for sticking PE or PVC material products, and it is not recommended for sticking on oily surfaces.

The above suggestion, application, and elaboration are not intended as the guarantee of Jinya. All sales of Jinya products shall be tested by customer in the final environment to confirm compliance with the requirements of the use of environment.

Printing Methods

The surface material has excellent ink absorption and is suitable for a variety of printing methods, including laser and inkjet printing. Matte paper with a rough surface, suitable for printing and printing of simple graphics. Used in office, and other industries.

Shelf life

12 months, applicable only to the material delivered by Jinya which has not undergone further processing, under the following **STORAGE CONDITIONS**:

- This material must be stored at a temperature of 23 ± 2°C and 50 ± 5% of Relative Humidity.
- Storage area must be dry and clean.
- Keep the material in the original packaging when not used in order to protect it from dust and contamination.
- Do not expose to direct sunlight or heat sources.