

## LLGHSL80-ER

### Face Material

weight	thickness	material
80 ± 2%g/m <sup>2</sup> ISO 536	0.083 ± 0.003%mm ISO 534	White smooth silicone topcoated paper

### Adhesive

8 ± 2 weight (g/m<sup>2</sup>)

### Adhesive

This is a removable acrylic adhesive with weak tack, not suitable for repeated peel-off application. Peel off without adhesive residue. Not suitable for PE bags and oily surface substrates, suitable for short-term applied on paper substrates.

### Peel adhesion

Initial adhesion 5N/25mm FTM 9 st.st	20 minutes Peel adhesion value on steel at 180° 3.5N/25mm or tear off FTM 1 st.st	20 minutes Peel adhesion value on steel at 90° 3N/25mm or tear off FTM 2 st.st
---	---	--

### Temperature

Min. Appl. Temp. 10 °C

Service Temp. 0°C+90°C (after 24hrs)

### Applications

Linerless label with weak adhesive for cashier paper and weak adhesive use.

The above suggestion, application, and elaboration are not intended as the guarantee of Jinya. All sales of Jinya products shall be tested by customer in the final environment to confirm compliance with the requirements of the use of environment.

### Printing Methods

The product has good performance on water, oil resistance and plasticizer resistance. It is suitable for the linerless paper thermal printing electronic scales and thermal printers. The initial viscosity and final viscosity of the product are high. Excellent viscous performance on packaging materials

### Shelf life

12 months, applicable only to the material delivered by Jinya which has not undergone further processing, under the following **STORAGE CONDITIONS**:

- This material must be stored at a temperature of 23 ± 2°C and 50 ± 5% of Relative Humidity.
- Storage area must be dry and clean.
- Keep the material in the original packaging when not used in order to protect it from dust and contamination.
- Do not expose to direct sunlight or heat sources.